

# SUPER RUSH GP

## General Purpose Cementitious Key Coat

### Description

**SUPER RUSH GP** is a polymer modified cementitious key coat with application of 2-3mm to provide high bonding for subsequent plaster layers. It is a ready to use mix that consisting of Portland cement, high strength synthetic binder, graded aggregates and chemical additives to formulate a high bond strength layer for application on smooth concrete walls and ceilings (not contain micro silica or GGBS) to work as a rough scratch coat before applying the cement plaster.

### Features & Benefits

- Enhance the adhesion and prevent hollow and peel off of plaster/ renders.
- Ready to use just require mixing with water
- Easy to apply and environment friendly
- Contains no chloride or sulphates additives
- For exterior and interior use

### Uses

- Provide rough key coat before applying plaster/ renders.
- Used on blocks, general cementitious substrates, precast fair face concrete (contains no Micro-silica or GGBS)
- For concrete smooth ceilings without the need to hack the substrate

### Technical Properties

Appearance	Granulated cement mix
Density	1,850 Kg/m <sup>3</sup> approx.
Compressive strength	25 N/mm <sup>2</sup> @ 28 days
Flexural Strength	4.5 N/mm <sup>2</sup> @ 28 days
Inflammability	None
Adhesion Strength	1.5 N/mm <sup>2</sup> @ 28 days
Pot Life	45 min @ 25 °C

All values are subject to 5-10% tolerance

### Standards Compliance:

- ASTM C150, C579, C580
- ASTM C926, C897
- BS EN 1015, 4551 Pt. 3& 7

### Application Procedures

#### Surface preparation:

Concrete surface must be free from dust, loosely adhered material, plaster and cement droppings, grease, oil, paints etc. The surface should be dampened down with water prior to the application of **SUPER RUSH GP**.

All curing compound films and shuttering oil should be removed to ensure good adhesion for the key coat.

#### Mixing Instructions:

To prepare the mixture, pour 10.5- 11 liters of clean water into container and add slowly the content of **SUPER RUSH GP** (50 Kg bag). Mix using spiral paddle in slow speed heavy duty drill for 3-5 minutes till a homogeneous lump free consistency mix is achieved. Always add powder to water and not the other way around.

Allow product to set for approximately 3-5 minutes then lightly re-stir before use.

#### Application Instructions:

Apply **SUPER RUSH GP** using suitable spraying unit or manually with Tyrolean machine. Spray an entire prepared area and allow sometime for the applied rush coat to stiffen before doubling back. **SUPER RUSH GP** should be applied in a total thickness of 2-3mm, ensure that **SUPER RUSH GP** covers the entire surface area. A rough texture is to be obtained to provide a mechanical key for subsequent coat of plaster. The applied layer should be water cured for minimum 2 days before applying the plaster.

## Yield/ Coverage

A 50kg bag of **SUPER RUSH GP** will cover up to 20 m<sup>2</sup> at coat thickness of 2mm.

## Packaging

**SUPER RUSH GP** is available in 50kg bag.

## Storage

Keep the product in dry and sheltered place at temperature between +5°C to +35°C. In these conditions and in closed original containers, the product will have a shelf life of at least 12 months.

## Health and Safety

Wear gloves, goggles to avoid any contact with eyes and skin. In case of splashes in the eyes wash abundantly with warm water and consult a doctor.

For further information or particular use, contact SBI Technical Department.

## Quality & Care

All products produced in SBI facilities are manufactured under a management system certified to conform to the requirements of the quality and environmental health & safety standards ISO 9001 & ISO 14001.

REV 00-3001

**SALES OFFICE** : Dubai, Barsha, Rasis Business Center  
**FACTORY** : RAK, Jazerat Al Hamra

Tel.+971 4 3999927  
Tel. +971 7 2210066  
Fax. +971 7 2433821  
P.O.Box 14569  
[www.sbi-me.com](http://www.sbi-me.com) , [info@sbi-me.com](mailto:info@sbi-me.com)